


MULTIGIPS

D100R48

RADIATION PROTECTION BLOCK



Solid gypsum block with smooth faces for non-load bearing partition walls in rooms with radiation protection requirements


D100-R48
High density (D) 1.4
100 mm thickness
Barythic
acc. to EN 12859

VG-ORTH GMBH & CO. KG
Holeburgweg 24
DE - 37627 Städtoldendorf
Phone +49 5532 505-0
Fax +49 5532 505-560
info@multigips.de

Up-to-dateness
MG | TM | D100-R48 | ENG | VGO | 07.21
ce.multigips.de

MULTIGIPS TECHNICAL DATA SHEET

Solid gypsum block
MultiGips D100-R48



MultiGips

Solid gypsum block with smooth faces for the construction of non-load bearing partition walls

High density

Technical Data Sheet contains informations according to the latest technical development. Only valid in conjunction with the recognized rules of construction technology and in conjunction with the technical documentation of VG-ORTH GmbH & Co. KG. Does not apply to other specified construction products/types in conjunction with their installation. Provides technical information for designers and users to improve their understanding and ensure that the construction product is used and applied as intended. Does not substitute compliance with the established rules of construction technology and professional use and design under practical conditions. Warranted performance by the manufacturer for the construction product at time of market introduction. No commitment to a legally binding guarantee of certain properties or suitability for a particular application. Performance characteristics of the applied construction product dependent on different conditions, e.g. weather, temperature, substrate inspection and pre-treatment, professional application and/or time for drying / hardening. The relevant technical values for the construction product were calculated in accordance with the testing standard. Consumption, volumes and times may deviate from test values under practical conditions. To achieve the physical, structural and construction properties of MultiGips gypsum blocks or gypsum building plasters, only MultiGips system components or products recommended by VG-ORTH GmbH & Co. KG may be used.

European Standard	
Term	
Quality assurance	
Use	
Scope	
Reaction to fire	
Resistance to fire	
Direct airborne sound insulation R_w weighted sound reduction index Rating acc. to EN ISO 717-1	
Dimensions, d/l/h	
Class of density	
Density, approx.	
Class of water absorption	
Water absorption (in water for 2 h)	
Bending strength, minimum average breaking load	
Surface hardness	
Mass per square metre, incl. components, approx.	
Assembling	

ARTICLE	ARTICLE GROUP
MultiGips D100-R48 28 kg 5 blocks/m ² wall	Solid gypsum block High density R48
Storage	
Hazards Identification	

EN 12859	
Gypsum block with tongues and grooves on at least two of their opposite edges and with plain and smooth surface intended to provide the finish of a partition	
Initial type testing and factory production control	
Construction of non-load bearing partition walls in rooms with radiation protection requirements	
In X-ray rooms for diagnostics and radiation therapy in healthcare buildings	
Non-combustible Class A1 (no contribution to fire) acc. to 96/603/EC	
EI 120 acc. to EN 13501-2 120 min. acc. to WF Report No 194213 Issue 4	
48 dB In conjunction with elastic interlayer MultiGips AkustikBit 1000 Without flanking transmission	
100/400/500 mm	
D (dense)	
1,400 kg/m ³ , reddish	
H3, no requirement	
No requirement	
> 9.4 kN	
> 80 Shore C	
142 kg/m ²	
Connect with gypsum adhesive for gypsum blocks acc. to EN 12860. Stability due to connection to adjacent building components. No plastering required. To create background for tiles, repel gypsum adhesive after hardening; do not fill surfaces. If necessary, protect metal parts against corrosion. Can be applied on raw floors or on suitable floating screed (at usual room heights and in compliance with sound insulation requirements). In conjunction with elastic interlayers (for Germany: in acc. with DIN 4103-2, Table 4). Install elastic interlayers between wall and adjacent components tightly butted and free of cavities. After surface filling of the wall, cut off elastic interlayers flush.	

PACKAGING UNIT	MATERIAL NUMBER	EAN
24 blocks/pallet 2 packages/pallet 672 kg/pallet 4.8 m ² /pallet	781	4003230006046
Dry on Euro pallets		
Not classified as hazardous acc. to regulation (EC) No 1272 (CLP) Observe safety data sheet: ce.multigips.de		